## Specifications

DECEMBER 2010

## FC-20/67

**APPLICATIONS:** Protective packaging

Scratch & abrasion resistant wrapping Source reduction through downgauging

Furniture covers

Temperature use to 180° F

**DESCRIPTION:** Coextruded film

Two sided sealing Superior tensile strength High dart impact

Antiblock free formulation

FDA approved

## **SPECIFICATIONS:**

Property	Units		1.5 mil	3.5 mil	5.5 mil
O2TR	cc/100 sq. inday-atm		325	125	75
VVVTR	g/100 sq. inday-atm		0.66	0.27	0.18
Dart	grams		800	1300	2000
Secant	Psia	MD	23000	26000	27000
modulus	Psia	TD	25000	26000	27000
Tensile	Psia	MD	7200	7300	6700
(at break)	%		600	690	700
	Psia	TD	7500	7300	7300
	%		700	710	740
Tear	grams	MD	630	1430	2580
	grams	TD	820	1810	2820

**A**VAILABILITY:

Bottom seal bags 30" - 60" wide, 20" - 100" deep Side seal bags 20" - 200" wide, 15" - 60" deep

Tubing 30" - 60" wide Single wound sheeting 10" - 60" wide Center fold sheeting 15" - 60" wide Thickness range 1.5 to 5.5 mils

Color natural



645 SOUTH HIGH STREET COVINGTON, OHIO 45318 P: 937.473.2051 F: 937.473.2403

W: WWW.GENERALFILMS.COM